

LAMPIRAN

SARINGAN		TERTAHAN		KUMUTAHAN		%KUM LOLOS		SPEKTRIKASI	
No	Diameter							Bawah	Atas
1	25.4	0	0	0	0.000	100.000		100	100
3/4	19.1	0	0	0	0.000	100.000		85	100
1/2	12.7	101.75	101.75	101.75	783	98.217		64	85
3/8	9.52	354.75	456.5	456.5	10.433	69.567		45	65
4	4.76	933.85	1390.35	1390.35	690	7.370		34	54
8	2.38	102.75	1493.1	1493.1	540	0.460		20	33
40	0.425	4.1	1497.2	1497.2	813	0.187		16	26
60	0.25	0.8	1498	1498	867	0.133		14	18
100	0.149	0.6	1498.6	1498.6	907	0.093		8	10
200	0.074	0.2	1499.5	1499.5	967	0.053			

GRABASI CAMKAMU SAWIT SET DI LOS ANGELES

SARINGAN		TERTAHAN		KUMUTAHAN		%KUM LOLOS	
No	Diameter						
1	25.4	0	0	0	0.000	100.000	
3/4	19.1	0	0	0	0.000	100.000	
1/2	12.7	13.9	13.9	13.9	0.927	99.073	
3/8	9.52	133.7	133.7	133.7	9.840	90.160	
4	4.76	811.0	811.0	811.0	63.967	36.033	
8	2.38	314	314	314	84.900	15.100	
40	0.425	180.9	180.9	180.9	96.980	3.020	
60	0.25	35.9	35.9	35.9	99.753	0.247	
100	0.149	5.8	5.8	5.8	99.740	0.260	
200	0.074	3.7	3.7	3.7	99.957	0.043	



GRADASI LAPANGAN CANGKANG SAWIT

SARINGAN		TERTAHAHAN	KUMTAHAN	%KUMTAHAN	%KUM LOLOS	SPESIFIKASI	
No	Diameter					Bawah	Atas
1	25.4	0	0	0.000	100.000	100	100
3/4	19.1	0	0	0.000	100.000	85	100
1/2	12.7	101.75	101.75	6.783	93.217		
3/8	9.52	354.75	456.5	30.433	69.567	65	85
4	4.76	933.85	1390.35	92.690	7.310	45	65
8	2.38	102.75	1493.1	99.540	0.460	34	54
40	0.425	4.1	1497.2	99.813	0.187	20	35
60	0.25	0.8	1498	99.867	0.133	16	26
100	0.149	0.6	1498.6	99.907	0.093	10	18
200	0.074	0.9	1499.5	99.967	0.033	5	10

GRADASI CANGKANG SAWIT SETELAH DI LOS ANGELES

SARINGAN		TERTAHAHAN	KUMTAHAN	%KUMTAHAN	%KUM LOLOS
No	Diameter				
1	25.4	0	0	0.000	100.000
3/4	19.1	0	0	0.000	100.000
1/2	12.7	13.9	13.9	0.927	99.073
3/8	9.52	133.7	147.6	9.840	90.160
4	4.76	811.9	959.5	63.967	36.033
8	2.38	314	1273.5	84.900	15.100
40	0.425	180.9	1454.4	96.960	3.040
60	0.25	35.9	1490.3	99.353	0.647
			16.1	99.740	0.260
			19.8	99.987	0.013




Repository University Of Riau

PERPUSTAKAAN UNIVERSITAS RIAU

<http://repository.unri.ac.id/>

KURVA GRADASI AGGREGAT GABUNGAN


SARINGAN		FRAKSI SARINGAN DAN ASLI CANGKANG SAWIT							Gab
No	Diameter	ASLI	4.76	2.380	0.425	0.25	0.149	0.075	
		49.29%	7.31%	9.62%	8.87%	6.97%	7.98%	9.95%	
1	25.4	100.000	100.000	100.000	100.000	100.000	100.000	100.000	100
3/4	19.1	100.000	100.000	100.000	100.000	100.000	100.000	100.000	100
3/8	9.52	69.567	100.000	100.000	100.000	100.000	100.000	100.000	85
4	4.76	7.310	0.000	100.000	100.000	100.000	100.000	100.000	47
8	2.38	0.460	0.000	0.000	100.000	100.000	100.000	100.000	34
40	0.425	0.187	0.000	0.000	0.000	100.000	100.000	100.000	25
60	0.25	0.133	0.000	0.000	0.000	0.000	100.000	100.000	18
100	0.149	0.093	0.000	0.000	0.000	0.000	0.000	100.000	10
200	0.074	0.033	0.000	0.000	0.000	0.000	0.000	100.000	9.97



Repository University Of Riau

PERPUSTAKAAN UNIVERSITAS RIAU

<http://repository.unri.ac.id/>



Repository University Of Riau

PERPUSTAKAAN UNIVERSITAS RIAU

<http://repository.unri.ac.id/>